

## TECHNICAL DATA SHEET

# SYNOLAC® S39X70

Short Oil Alkyd

### PRODUCT APPLICATION DETAILS

SYNOLAC® S39X70 is a semi drying short oil alkyd resin. It can be used as plasticizing resin in NC paint. In conjunction with proper amino resins, acid curing lacquers with good pot-life and cold check resistance properties can be formulated.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C, %)	69 - 71	ISO 3251
Viscosity (25°C at 60% NV, Gardner)	Z3Z4 - Z5	Gardner-Holdt
Color (Gardner)	Max. 4	ASTM D-1544
Acid value (mg KOH/g)	Max. 10	ISO 2114

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Density (25°C, g/mL)	1.05	-
Fatty acid type	Soya Bean Oil	-
Fatty acid content (%)	33	-
Hydroxyl content (%)	3.7	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Industrial Coating
  - General Industry
  - Wood Furniture

### PERFORMANCE BENEFITS

- Good plasticizing properties
- Fast drying
- Good sanding properties
- Good hardness

# SYNOLAC® S39X70

## FORMULATION GUIDELINES

### RECOMMENDATIONS FOR USE

SYNOLAC® S39X70 is recommended for use in furniture wood coatings. It can be used for acid curing when formulated together with amino resins. Use with isocyanate resin, it can be made into 2 pack polyurethane paint.

SYNOLAC® S39X70 give good hardness and fast drying time. It can be used for clear lacquer and pigmented coating. It can also be used for air drying paints by proper formulate with catalyst.

### SOLUBILITY

Aromatic hydrocarbon — Complete

Ester — Complete

Ketone — Complete

Alcohol — Partial

Aliphatic Hydrocarbon — Not Soluble

### COMPATIBILITY

Urea Resins — Very Good

Short Oil Alkyd — Good

Melamine Resins — Good

Polyester Resins — Fair

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOLAC® S39X70 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

**Arkema Coating Resins Malaysia**  
PLO 491, Jalan Keluli, Pasir Gudang  
Industrial Estate, 81700 Pasir Gudang,  
Johor – Malaysia  
T +60 7 253 6688

**Headquarter: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**