

## TECHNICAL DATA SHEET

# SYNOLAC® T49MP

*Short Oil Alkyd*

### PRODUCT APPLICATION DETAILS

SYNOLAC® T49MP is semi-drying alkyd resin. Used in conjunction with suitable amino resins, high solids acid curing finishes with low aromatic solvents can easily be formulated. System based on SYNOLAC® T49MP give high film build, good stackability and good chemical and wet heat resistance.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C, %)	82 - 86	ISO 3251
Viscosity (25°C, Gardner)	Z5 - Z6	Gardner-Holdt
Color (Gardner)	Max. 6	ASTM D-1544
Acid value (mg KOH/g)	18 - 30	ISO 2114

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Methoxy Propanol	-
Density (25°C, g/mL)	1.07	-
Fatty acid type	Tall Oil Fatty Acid	-
Fatty acid content (%)	49	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Industrial Coating
  - Wood Furniture
  - Wood Parquet

### PERFORMANCE BENEFITS

- Excellent wet heat resistant
- High film build
- Low aromatic content
- Good gloss
- Good stackability

# SYNOLAC® T49MP

## FORMULATION GUIDELINES

### RECOMMENDATIONS FOR USE

SYNOLAC® T49MP is recommended for use in furniture and parquet finishes particularly acid curing and nitro-cellulose system. It is suite from coating that high solids, high build and low aromatics.

### SOLUBILITY

Aromatic hydrocarbon — Complete  
Ester — Complete  
Ketone — Complete  
Glycol Ether — Complete  
Alcohol — Partial  
Aliphatic Hydrocarbon — Partial

### COMPATIBILITY

Urea Resins — Very Good  
Isocyanate Resins — Very Good  
Short Oil Alkyd — Good  
Melamine Resins — Good  
NC/CAB — Good  
Polyester Resins — Fair  
Acrylic Resins — Fair  
Epoxy Resins — Fair

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOLAC® T49MP should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.  
In the above mentioned storage conditions the shelf life of the resin will be 12 months.

**Arkema Coating Resins Malaysia**  
PLO 491, Jalan Keluli, Pasir Gudang  
Industrial Estate, 81700 Pasir Gudang,  
Johor – Malaysia  
T +60 7 253 6688

**Headquarter: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**