

TECHNICAL DATA SHEET

SYNOLAC® T62

Long oil alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® T62 is a long oil oxidizing alkyd develops for use in all decorative and marine paints/varnishes.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C, %)	58 - 62	ISO 3251
Viscosity (25°C, Gardner)	Z1 - Z2	Gardner-Holdt
Color (Gardner)	Max. 6	ASTM D-1544
Acid value (mg KOH/g)	5 - 8	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	White Spirit	-
Density (25°C, g/mL)	0.93	-
Fatty acid type	Tall Oil Fatty Acids	-
Fatty acid content (%)	62	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Primers
 - Trim
- Industrial Coating
 - Protective And Marine Coating

PERFORMANCE BENEFITS

- Fast drying
- Good durability
- Good color retention
- Good gloss retention

SYNOLAC® T62

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOLAC® T62 is a very suitable for use in both white and coloured paints exterior as well as interior. SYNOLAC® T62 is also very suitable to be used in marine paints. It can be used for most substrates. Paints based on SYNOLAC® T62 are more often applied by brush or roller.

A suitable combination of driers for use with SYNOLAC® T62 is 0.05% cobalt, 0.15% zirconium and 0.20% calcium calculated as metals on solid resin. Slight variations in the drier levels may be appropriate for particular paint systems.

To prevent in-can skinning of coatings a volatile anti-skinning agent such as methyl ethyl ketoxime is recommended. A level 0.2-0.5% calculated on solid resin is normally adequate.

SOLUBILITY

Aromatic hydrocarbon — Complete

Aliphatic Hydrocarbon — Complete

Alcohol — Partial

COMPATIBILITY

Long Oil Alkyd — Very Good

Linseed Oil — Very Good

Stand Oil — Very Good

Medium Oil Alkyd — Partial

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® T62 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

Arkema Coating Resins Malaysia
PLO 491, Jalan Keluli, Pasir Gudang
Industrial Estate, 81700 Pasir Gudang,
Johor – Malaysia
T +60 7 253 6688

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA