

TECHNICAL DATA SHEET

UNITHANE® 373 X 60

Modified alkyd

PRODUCT APPLICATION DETAILS

UNITHANE® 373 X 60 is a very fast drying, urethane modified, short oil alkyd especially for combinations with polyvinylchloride copolymers.

UNITHANE® 373 X 60 is particularly suited to the manufacture of protective coatings for industrial use in combination with PVC-copolymers, e.g. for agricultural machines, containers or chassis paints.

UNITHANE® 373 X 60 distinguishes by its very rapid drying and quick development of hardness even in thick films. Dry films show a good adhesion, water resistance and excellent anti corrosive properties. Combinations with PVC-copolymers, achieve an excellent chemical resistance and a minimum permeability for water vapour.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	59 - 61 %	ISO 3251
Reduced viscosity (4mm, 50% in Xylene) (20°C)	120 - 150 s	DIN 53 211
Color (Iodine Colour index) (50% in Xylene)	5 max	DIN EN 1557
Acid value	3 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Viscosity (Brookfield RVT , 20rpm)	4000 mPa.s	ISO 2555
Solvent	Xylene	-
Flash point	23 °C	ISO 3679
Density	1.00 g/ml	ISO 2811
Fatty acid type	Drying, vegetable fatty acids	-
Fatty acid content	37 %	-
Modification	Urethane	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry
 - Protective And Marine Coating

UNITHANE® 373 X 60

FORMULATION GUIDELINES

DRIERS

UNITHANE® 373 X 60 shows an excellent drying with 0,02% - 0.04% cobalt and 0.6% - 0.9% zirconium (metal on solid resin). Depending on the formulation (clear, pigmented, thixotropic, etc...) and on the application, the loading of each drier may be increased or reduced in order to achieve the appropriate drying/hardness profile.

The use of antiskinning agent is essential to prevent in-can skinning of the finished product.

SOLUBILITY

UNITHANE® 373 X 60 is completely soluble in aromatic hydrocarbons, esters, ketones and partially soluble in low flash point white spirit and alcohols.

COMPATIBILITY

UNITHANE® 373 X 60 is compatible with many short- and medium-oil alkyds, like SYNOLAC® 271 X 60, 272 X 60, 385 X 60, Laroflex® series ⁽¹⁾, Laropal® K80 ⁽¹⁾ and nitrocellulose. It is incompatible with long-oil alkyds and styrenated alkyds.

UNITHANE® 373 X 60 can easily be pigmented with titanium dioxide pigments and most inorganic and organic colour pigments. In anticorrosive systems zinc phosphate pigments can be used.

Notes: ⁽¹⁾ BASF

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

UNITHANE® 373 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790