

SYNOCURE® 852 BA 80

GENERAL INDUSTRY / PROTECTIVE & MARINE COATINGS

ARKEMA COATING RESINS

Product Application details

SYNOCURE® 852 BA 80 is a high solids hydroxy functional acrylic resin designed for curing at both room temperature and under low bake conditions with suitable polyisocyanates.

Ease of application, initial gloss and appearance make them suitable for many applications including A.C.E. and general metal coatings. Coatings based on SYNOCURE® 852 BA 80 are faster drying than most other high solids types.

The high solids / low viscosity character of SYNOCURE® 852 BA 80 allows low VOC coatings to be formulated even with conventional polyisocyanates. Depending upon formulation <420g/l at 23 seconds cup 4 and <350g/l at 45 seconds are possible.

Polymer Type

- Solventborne Acrylic

Sales Specifications

Solid Content at 125°C, % (ISO 3251)	78 - 82
Viscosity at 25°C, mPa.s (ISO 12058-1)	6000 - 9000
Colour, Hazen scale (ISO 6271)	300 max
Acid value, mg KOH/g (ISO 2114)	10 max

Other Characteristics¹

Volatile	Butyl acetate
Flash point, °C (ISO 3679)	23
Density / Specific Gravity at 20°C, g/ml (ISO 2811)	1.035
Hydroxyl Content, %	4.1
Hydroxyl Equivalent weight	415

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

SYNOCURE® 852 BA 80 should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

$$\text{Hydroxyl equivalent weight} = \frac{17 \times 100}{\% \text{ OH}}$$

$$\text{Isocyanate equivalent weight} = \frac{42 \times 100}{\% \text{ NCO}}$$

Using Desmodur® N 75 series (1) or Tolonate™ HDB 75 MX (2), the recommended ratios would be:

	on solid resin	as supplied
SYNOCURE® 852 BA 80	415	519
Desmodur® N 75 series (1) or Tolonate™ HDB 75 MX (2)	191	255

The high reactivity of systems based on SYNOCURE® 852 BA 80 makes them ideal for use in coatings applied with twin-feed guns. When conventional application equipment is used care should be taken to mix no more paint than can be applied during the period appropriate to the pot life and to clean equipment immediately after use.

Formulation Guidelines

SYNOCURE®
BY ARKEMA

If necessary the initial rate of cure of SYNOCURE® 852 BA 80 based systems can be accelerated by the use of tin catalyst in the form of dibutyl tin dilaurate. Although the level can be varied to suit specific requirements 0.01-0.015% metal based on total solid resin is a good starting point.

SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 852 BA 80 should be free of water and should not contain groups that react with isocyanates. Esters and ketones are true solvents for this type of system and are recommended for use in conjunction with aromatic hydrocarbon diluents such as xylene.

Notes: (1) Bayer MaterialScience, (2) Vencorex Chemicals

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOCURE® 852 BA 80 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months from the shipping date

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY