

SYNOCURE® 899 BA 70 LM

PROTECTIVE & MARINE COATINGS

ARKEMA COATING RESINS

Product Application details

SYNOCURE® 899 BA 70 LM is a high solids content epoxy acrylic copolymer curing agent designed specifically for use with the Arkema range of SYNOCURE® acid and amine functional acrylic resins for the formulation of high quality isocyanate-free 2-component industrial coatings.

SYNOCURE® 899 BA 70 LM is a lower molecular weight variant of SYNOCURE® 899 BA 60. When used in combination with the regular solids acrylics, SYNOCURE® 890 S 55 and SYNOCURE® 895 S 55, benefits of improved solids and reduced VOC can be achieved.

Polymer Type

- Solventborne Epoxy Acrylic Copolymer

Sales Specifications

Solid Content at 125°C, % (ISO 3251)	68 - 72
--------------------------------------	---------

Viscosity at 25°C, mPa.s (ISO 3219)	450 - 850
-------------------------------------	-----------

Colour, Hazen scale (ISO 6271)	200 max
--------------------------------	---------

Other Characteristics¹

Volatile	Butyl acetate
----------	---------------

Flash point, °C (ISO 3679)	24
----------------------------	----

Density / Specific Gravity at 20°C, g/ml (ISO 2811)	1.04
---	------

Typical weight per epoxide (relative to solid resin)	415
--	-----

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

Formulation Guidelines

RECOMMENDATIONS FOR USE

Maximum high solids benefit and low VOC compliance (< 420 g/l) can be achieved when used with the high solids acrylic, SYNOCURE® 892 BA 70. This combination produces low VOC, fast drying 2-component isocyanate free coating systems for high durability enamels suitable for heavy duty, maintenance and transport applications. The technical data sheets describing SYNOCURE® 890 S 55, SYNOCURE® 895 S 55 and SYNOCURE® 892 BA 70 give details of the recommended mixing ratios and other formulating considerations. Further information on use may be found in the brochure 'Non-Isocyanate Acrylic resins for 2K Coatings' available from Arkema Coating Resins. SYNOCURE® 899 BA 70 LM is designed exclusively for use with the acrylic resins specified and should not be used in other non-isocyanate systems. SYNOCURE® 899 BA 70 LM should only be used in applications consistent with the above recommendations. Proposals to use the resin in any other way should be discussed with Arkema before any action is taken.

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOCURE® 899 BA 70 LM should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 6 months from the shipping date

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY