

SYNOLAC® 1421 WD 50

GENERAL INDUSTRY / ARCHITECTURAL COATINGS

ARKEMA COATING RESINS

Product Application details

SYNOLAC® 1421 WD 50 is a medium oil alkyd resin designed for use in decorative coatings. SYNOLAC® 1421 WD 50 is particularly adapted to the formulation of glossy varnishes and paints with a good weathering resistance. It is also convenient for fast drying anticorrosive primers formulations. It may also be used in combination with long oil alkyd resins to improve their drying.

Polymer Type

- Solventborne Alkyd

Sales Specifications

Solid Content at 125°C, % (ISO 3251)	49 - 51
Viscosity at 25°C, mPa.s (Brookfield SC4-21/13R, 3.7 s-1) (ISO 3219)	8000 - 14000
Colour, Gardner scale (ISO 4630)	6 max
Acid value, mg KOH/g (ISO 2114)	10 max

Other Characteristics¹

Volatile	Low aromatic white spirit
Flash point, °C (ISO 3679)	42
Density / Specific Gravity at 25°C, g/ml (ISO 2811)	0.905
Type of fatty acid	linseed
Fatty Acid content, %	48

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

Formulation Guidelines

DRIERS

SYNOLAC® 1421 WD 50 requires metal driers to accelerate the autoxidation process. Surface and through drying can be achieved using a combination drier based on cobalt, zirconium and calcium. Expressed as metal percentage on dry alkyd, a convenient ratio might be: 0.05% cobalt, 0.15% zirconium and 0.2% calcium. Depending on the formulation (clear, pigmented, thixotropic, etc...) and on the application, the loading of each drier may be increased or reduced in order to achieve the appropriate drying/hardness profile.

The use of an anti-skinning agent such as methyl ethyl ketoxime is essential to prevent in-can skinning of the finished product.

SOLUBILITY

SYNOLAC® 1421 WD 50 is soluble in aromatic and aliphatic hydrocarbons, esters and partially soluble in alcohols.

COMPATIBILITY

SYNOLAC® 1421 WD 50 is compatible with most long oil and medium oil alkyd resins. Its compatibility with short oil alkyds might be limited, dependent on the ratio and should be checked before use.

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® 1421 WD 50 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C.
Exposure to direct sunlight should be avoided.
Under the above mentioned storage conditions the shelf life of the resin will be 9 months from the shipping date.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY