

SYNOLAC® 272 X 60

GENERAL INDUSTRY

ARKEMA COATING RESINS

Product Application details

SYNOLAC® 272 X 60 is a fast drying, short-oil alkyd for air drying and stoving systems. SYNOLAC® 272 X 60 is universally suitable for a wide range of air drying industrial coatings, like fast drying primers, fillers, single layer coatings and finishes. In combination especially with highly reactive amino formaldehyde resins stoving systems, particularly drum coatings, may be formulated.

Performance Benefits

- Very fast drying
- Good solvent release
- Good balance of hardness and flexibility
- Good gloss
- Excellent yellowing resistance

Polymer Type

- Solventborne Alkyd

Sales Specifications

Solid Content at 125°C, % (ISO 3251)	59 - 61
Reduced Viscosity at 20°C, s (4mm, 50% in Xylene) (DIN 53 211)	110 - 130
Iodine Colour index, (50% in Xylene) (DIN EN 1557)	10 max
Acid value, mg KOH/g (ISO 2114)	10 max

Other Characteristics¹

Viscosity at 23°C, mPa.s (Brookfield) (ISO 3219)	2500 - 3000
Volatile	Xylene
Flash point, °C (ISO 3679)	24
Density / Specific Gravity at 20°C, g/ml (ISO 2811)	1.02
Type of fatty acid	Vegetable fatty acids
Hydroxyl Content, %	2.0

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

Formulation Guidelines

RECOMMENDATIONS FOR USE

SYNOLAC® 272 X 60 can also be combined with aliphatic or aromatic polyisocyanates to formulate two-pack systems.

Primers based on SYNOLAC® 272 X 60 maintain a good recoatability particularly when formulated without metal driers. Stoving systems with highly reactive melamine formaldehyde resins show a good cure response even at relatively low temperatures.

SYNOLAC® 272 X 60 is compatible with various PVC-copolymers making it suitable also for the formulation of very fast drying primers and single layer coatings with excellent anti-corrosive performance.

SYNOLAC® 272 X 60 can be easily pigmented with titanium dioxide pigments and most inorganic and organic colour pigments. In anti-corrosive systems the use of zincphosphates is recommended.

In primer formulations the use of driers is often not required with SYNOLAC® 272 X 60. However, with additions of 0.03% cobalt (metal on solid resin) the initial hardness can be improved. In finishes a combination of 0.02% - 0.03% cobalt with 0.4% - 0.6% zirconium (calculated as metals on solid resin) is recommended. Depending on the formulation (clear, pigmented, thixotropic, etc..) and on the application, the loading of each drier may be increased or reduced in order to achieve the appropriate drying/hardness profile.

The use of antiskinning agent is essential to prevent in-can skinning of the finished product.

SOLUBILITY

SYNOLAC® 272 X 60 is completely soluble in aromatic hydrocarbons, esters, glycol ethers, glycol ether esters, ketones. It is partially soluble in alcohols and aliphatic hydrocarbons.

COMPATIBILITY

SYNOLAC® 272 X 60 is compatible with short oil and some medium oil alkyds like SYNOLAC® 271 X 60, non-plasticized urea- and melamine formaldehyde resins, Resamin® HF 450 (1), adhesion resin LTW (2), nitrocellulose, ketone resins and some PVC-copolymers, like the Laroflex® series (3) types of products. It is partially compatible with Epikote™ Resin 1001 (4) and some PVC-copolymers and incompatible with epoxy esters and styrenated alkyds.

Notes: (1) Cytec, (2) Evonik Industries AG, (3) BASF, (4) Momentive

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® 272 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

Under the above mentioned storage conditions the shelf life of the resin will be 9 months from the shipping date.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY