

SYNOLAC® 5201 X 55

GENERAL INDUSTRY

ARKEMA COATING RESINS

Product Application details

SYNOLAC® 5201 X 55 is an acrylic modified short oil alkyd resin recommended for fast air drying and low bake industrial coatings. Application and overcoating properties are exceptionally good for a resin of this type.

Performance Benefits

- Good gloss
- Good colour
- Good colour retention
- Good adhesion
- Good flexibility

Polymer Type

- Solventborne Alkyd

Sales Specifications

Solid Content at 125°C, % (ISO 3251)	53.5 - 56.5
Viscosity at 25°C, mPa.s (Brookfield SC4-25/13R, 13.2s-1) (ISO 3219)	1400 - 1800
Colour, Gardner scale (ISO 4630)	7 max
Acid value, mg KOH/g (ISO 2114)	18 max

Other Characteristics¹

Volatile	Xylene
Flash point, °C (ISO 3679)	25
Density / Specific Gravity at 25°C, g/ml (ISO 2811)	0.99
Type of fatty acid	Fatty acids linoleic rich
Fatty Acid content, %	25
Modification	Acrylic monomers

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

DRIERS

For SYNOLAC® 5201 X 55, a suitable recommendation for drier modification is 0.01-0.03% cobalt as metal on solid resin. Depending on the formulation (clear, pigmented, thixotropic, etc...) and on the application, the loading of the drier may be increased or reduced in order to achieve the appropriate drying/hardness profile.

The use of antiskinning agent is essential to prevent in-can skinning of the finished product.

Formulation Guidelines

SOLUBILITY

SYNOLAC® 5201 X 55 is completely soluble in aromatic hydrocarbons, esters, ketones and glycol ethers and has a limited solubility in aliphatic hydrocarbons and alcohols.

COMPATIBILITY

SYNOLAC® 5201 X 55 is completely compatible with some styrenated alkyd resins, amino resins, hard resins, short oil alkyd resins and nitrocellulose.

It has a limited compatibility with some medium oil length alkyd resins, acrylic copolymers and some epoxy esters.

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® 5201 X 55 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

Under the above mentioned storage conditions the shelf life of the resin will be 6 months from the shipping date.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY