

SYNOLAC® 5387 X 60

GENERAL INDUSTRY

ARKEMA COATING RESINS

Product Application details SYNOLAC® 5387 X 60 is a special epoxy ester, with a quick air drying, hardness development and a fast recoatability. This resin is essentially designed for the preparation of anticorrosive primers.

Performance Benefits

- Resistance to abrasion
- Chemical resistance
- Adhesion on difficult substrates (copper, zinc, aluminium...)
- Good mechanical properties

Polymer Type

- Solventborne Alkyd

Sales Specifications

Solid Content %	58.5 - 61.5
Viscosity at 20°C, dPa.s (Noury)	30 - 50
Colour, Gardner scale (50% % in solvent)	8 max

Other Characteristics¹

Acid value, mg KOH/g	4 max
Volatile	Xylene
Density / Specific Gravity, g/ml	1.07
Fatty Acid content, %	40

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

SYNOLAC® 5387 X 60 exhibits particular properties in order to formulate:

- primers with high initial hardness and short recoverability (20 minutes to 3 days),
- air drying alkyd resin finishes,
- amino resin or 2 components PU stoving finishes, without surface defects.

$P / B = 35.2 / 17.58 = 2 / 1$

Films applied by spray (dry thickness 30 to 35 microns) show:

- aspect: matt - satin
- drying: dust free time = 8 - 10 minutes
handleable = 15 minutes
paper = 20 minutes
- hardness: 24h = 150 seconds
48 h = 160 seconds
5 days = 180 seconds
15 days = 185 seconds
- reverse impact: 1 kg / 30 cm = OK
- recoatability: between 20 minutes to 3 days after the application, this primer can be recoated at any time with a top coat (diluted in naphtha solvents or a 2 components PU top coat).

Formulation Guidelines

Example for primer formulation:

Iron oxide (red)	8.8
Talc 10 microns	8.8
Barium sulfate	17.6
SYNOLAC® 5387 X 60	29.3
drier	1.5
xylene	34.0
-----	-----
TOTAL	100.0

SOLUBILITY

SYNOLAC® 5387 X 60 is soluble in aromatic hydrocarbons, terpenics and chlorinated solvents, in esters and ketones, in glycol ethers. Aliphatic hydrocarbons and alcohols are not solvent of this resin, but alcohols can be used in small quantities to reduce the viscosity.

COMPATIBILITY

SYNOLAC® 5387 X 60 is compatible with melamine resins for stoving coatings as well as with some ethylcellulose for the air drying or stoving.

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® 5387 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

Under the above mentioned storage conditions the shelf life of the resin will be 6 months from the shipping date.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY