

SYNOLAC® 8236 X 55

(FORMERLY E 20836)

GENERAL INDUSTRY

ARKEMA COATING RESINS

Product Application details SYNOLAC® 8236 X 55 is a short oil epoxy ester used in air drying and stoving primers and finishes for a wide variety of applications.

Performance Benefits

- Excellent toughness and flexibility
- Excellent chemical resistance
- Good adhesion

Polymer Type

- Solventborne Alkyd

Sales Specifications	Solid Content at 125°C, % (ISO 3251)	53 - 57
	Viscosity at 25°C, mPa.s (ISO 3219)	1500 - 3200
	Colour, Gardner scale (ISO 4630)	6 max
	Acid value, mg KOH/g (ISO 2114)	6 max

Other Characteristics¹	Volatile	Xylene
	Flash point, °C (ISO 3679)	26
	Density / Specific Gravity at 25°C, g/ml (ISO 2811)	0.96
	Type of fatty acid	Linoleic rich

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

SYNOLAC® 8236 X 55 is particularly suitable for use in air drying primers where good anticorrosive properties are essential and in automobile stoving primers where high performance in terms of adhesion and chemical resistance are desirable. The use of 5% - 15% of melamine resin on total resin content will give an increased rate of cure in stoving systems.

The excellent resistance of SYNOLAC® 8236 X 55 to acids and alclis can be used to advantage in air drying and stoving finishes for application by spraying. Bronze finishing is one typical air drying application and paints for bicycle frames are typical of the use made of the resin in stoving finishes.

DRIERS

For air drying applications 0.04% cobalt, calculated as metal on solid resin, is recommended. In highly pigmented systems up to 0.1% calcium may be used. In stoving systems 0.01% cobalt or 0.02% manganese may be employed.

Depending on the formulation (clear, pigmented, thixotropic, etc...) and on the application, the loading of each drier may be increased or reduced in order to achieve the appropriate drying hardness profile.

SOLUBILITY

SYNOLAC® 8236 X 55 is soluble in aromatic hydrocarbons, ketones and esters. The resin has limited solubility in aliphatic hydrocarbons and alcohols.

COMPATIBILITY

SYNOLAC® 8236 X 55 is compatible with amino resins and some short oil alkyds.

Formulation Guidelines

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® 8236 X 55 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 6 months from the shipping date

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY