

SYNOCURE® 878 N 60 MY

Hydroxyl Functional Acrylic, 2.7% OH

ARKEMA COATING RESINS

Product Application details

SYNOCURE® 878 N 60 MY is a hydroxy functional acrylic resin designed to crosslink at room temperature with polyisocyanates.

SYNOCURE® 878 N 60 MY is particularly well suited for use in high quality industrial coatings. The excellent adhesion properties make the resin a good choice for primers, fillers and single coat paints for a variety of substrates. Steel, galvanised steel, aluminium, wood, plastic and minerals can all be coated satisfactorily using coatings based on SYNOCURE® 878 N 60 MY.

SYNOCURE® 878 N 60 MY has good resistance properties to solvents and chemicals and to exposure to weather and UV light, making it suitable for high quality anti-corrosive protection and for long life decorative coatings, especially on structural steelwork.

Performance Benefits

- Excellent chemical and stain resistance
- Good durability
- Excellent adhesion
- Economy in use

Polymer Type

- Solventborne Acrylic

Sales Specifications

Solid Content at 125°C, % (ISO 3251)	59 - 61
Viscosity at 25°C, mPa.s (ISO 3219)	1900 - 2800
Colour, Hazen scale (ISO 6271)	100 max
Acid value, mg KOH/g (ISO 2114)	5 - 10

Other Characteristics¹

Volatile	aromatic hydrocarbon, boiling range 160°C-180°C
Density / Specific Gravity at 20°C, g/ml (ISO 2811)	0.99
Hydroxyl Content, %	2.7
Hydroxyl Equivalent weight	630

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

SYNOCURE® 878 N 60 MY should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

$$\text{Hydroxyl equivalent weight} = \frac{17 \times 100}{\% \text{ OH}}$$

$$\text{Isocyanate equivalent weight} = \frac{42 \times 100}{\% \text{ NCO}}$$

Using Tolonate™ HDB 75 series (1) or Desmodur® N 75 series (2), the recommended ratios would be:

Formulation Guidelines

	on solid resin	as supplied
SYNOCURE® 878 N 60 MY	630	1050
Tolonate™ HDB 75 series (1) or Desmodur® N 75 series (2)	191	255

SYNOCURE® 878 N 60 MY reacted with Tolonate™ HDB 75 series (1) or Desmodur® N 75 series (2) in stoichiometric proportions has a usable pot life in excess of a full working day at normal room temperatures. The use of catalysts or higher temperatures will reduce this storage period.

To increase the initial rate of cure of SYNOCURE® 878 N 60 MY paints, at both ambient temperatures and under low bake conditions, the use of tin or zinc catalysts in the form of dibutyl tin dilaurate or zinc octoate is recommended. The levels used will depend on specific requirements, but typical metal contents calculated on total solid resin would be 0.001% tin and 0.0015% zinc.

SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 878 N 60 MY should be free of water and should not contain groups which react with isocyanates. Esters and ketones are true solvents for this type of system and are usually used with aromatic hydrocarbon diluents.

Notes: (1) Vencorex Chemicals, (2) Covestro

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOCURE® 878 N 60 MY should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins Malaysia Sdn Bhd

PLO 491, Jalan Keluli, Pasir Gudang Industrial Estate,

81700 Pasir Gudang, Johor, Malaysia.

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY