

SYNOLAC® T62

Long Oil Alkyd

ARKEMA COATING RESINS

Product Application details SYNOLAC® T62 is a long oil oxidizing alkyd develops for use in all decorative and marine paints/varnishes.

Performance Benefits

- Fast drying
- Good durability
- Good color retention
- Good gloss retention

Polymer Type

- Solventborne alkyd

Sales Specifications

Solid Content at 125°C, % (ISO 3251)	58 - 62
Viscosity at 25°C, Gardner Holdt	Z1 – Z2
Colour, Gardner scale (ASTM D1544)	6 max
Acid value, mg KOH/g (ISO 2114)	5 - 8

Other Characteristics¹

Volatile	White Spirit
Density / Specific Gravity at 25°C, g/ml (ISO 2811)	0.93
Type of oil / fatty acid	Tall Oil Fatty Acid
oil / fatty acid content, %	62

Note: Acid value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

SYNOLAC® T62 is a very suitable for use in both white and coloured paints exterior as well as interior. SYNOLAC® T62 is also very suitable to be used in marine paints. It can be used for most substrates. Paints based on SYNOLAC® T62 are more often applied by brush or roller.

A suitable combination of driers for use with SYNOLAC® T62 is 0.05% cobalt, 0.15% zirconium and 0.20% calcium calculated as metals on solid resin. Slight variations in the drier levels may be appropriate for particular paint systems.

To prevent in-can skinning of coatings a volatile anti-skinning agent such as methyl ethyl ketoxime is recommended. A level 0.2-0.5% calculated on solid resin is normally adequate.

Formulation Guidelines

SOLUBILITY

Aromatic hydrocarbon	Complete
Aliphatic Hydrocarbon	Complete
Alcohol	Partial

COMPATIBILITY

Long Oil Alkyd	Very Good
Linseed Oil	Very Good
Stand Oil	Very Good
Medium Oil Alkyd	Partial

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® T62 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins Malaysia Sdn Bhd

PLO 491, Jalan Keluli, Pasir Gudang Industrial Estate,

81700 Pasir Gudang, Johor, Malaysia.

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY