

SYNOLAC[®] 40X60 MY

MODIFIED ALKYD

ARKEMA COATING RESINS

Product Application details

SYNOLAC[®] 40X60 MY is a styrenated short oil alkyd resin modified with dehydrated castor and soya oils. SYNOLAC[®] 40X60 MY is recommended for very fast air drying spraying finishes, water and mineral oil resistant finishes and primers for crankcases.

Performance Benefits

- Very fast initial and hard drying
- Good resistance to water and mineral oils

Polymer Type

- Solventborne Alkyd

Sales Specifications

Solid Content at 125°C, % (ISO 3251)	59 - 61
Viscosity at 25°C, Gardner Holdt	XY – Z+
Colour, Gardner scale (ASTM D1544)	6 max
Acid value, mg KOH/g (ISO 2114)	15 max

Other Characteristics¹

Volatile	Xylene
Density / Specific Gravity at 25°C, g/ml (ISO 2811)	1.00
Type of fatty acid	Dehydrated castor / soya
Fatty Acid content, %	36
Modification	Styrene

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

Formulation Guidelines

DRIERS

The recommended drier level for use on air drying systems is 0.03% cobalt as metal on solids resin. Depending on the formulation (clear, pigmented, thixotropic, etc...) and on the application, the loading of each drier may be increased or reduced in order to achieve the appropriate drying/hardness profile.

The use of antiskinning agent is essential to prevent in-can skinning of the finished product.

SOLUBILITY

SYNOLAC[®] 40X60 MY is soluble in aromatic hydrocarbons, esters, ketones and glycol ethers. Its solubility is limited in terpenics. It is insoluble in alcohols.

COMPATIBILITY

SYNOLAC[®] 40X60 MY is compatible with hydrocarbons resins, partially compatible with drying oils, maleic resins and modified phenolic resins. It is incompatible with standoils, long and medium oil alkyd resins, melamine/formaldehyde resins and chlorinated rubber resins.

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® 40X60 MY should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C.

Exposure to direct sunlight should be avoided.

Under the above mentioned storage conditions the shelf life of the resin will be 12 months.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins Malaysia Sdn Bhd

PLO 491, Jalan Keluli, Pasir Gudang Industrial Estate,

81700 Pasir Gudang, Johor, Malaysia.

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY