

SYNOLAC[®] 133A

SHORT OIL ALKYD

ARKEMA COATING RESINS

Product SYNOLAC[®] 133A is a non-drying short oil alkyd based on coconut oil. Outstanding features of
Application details SYNOLAC[®] 133A include good gloss, good flexibility, good adhesion and non-yellowing.

Performance Benefits

- Good gloss
- Good flexibility
- Good adhesion
- Non-yellowing

Polymer Type

- Solventborne Alkyd

Sales Specifications

Solid Content % (ISO 3251)	59 - 61
Viscosity at 25°C, Gardner Holdt	(Z5-) – (Z5+)
Colour, Gardner scale (ASTM D1544)	5 max
Acid value, mg KOH/g (ISO 2114)	15 max

Other Characteristics¹

Volatile	Solvesso 150
Density / Specific Gravity at 25°C, g/ml (ISO 2811)	1.04
Type of fatty acid	Coconut Oil
Fatty Acid content, %	33

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

For air drying drum coatings, a combination of 0.02% Cobalt and 0.1% Zinc expressed as metals on solid resin is recommended. Methyl ethyl ketoxime at 0.08% of the weight of paint is recommended as anti-skinning agent in paints containing driers.

For stoving drum coatings, urea resin up to 30% or Melamine resin up to 20% calculated as percentage of total resin solids is recommended.

Formulation Guidelines

SOLUBILITY

Aromatic hydrocarbon	Complete
Ester	Complete
Ketone	Complete

COMPATIBILITY

Amino Resins	Very Good
Short Oil Alkyd	Good

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® 133A should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins Malaysia Sdn Bhd

PL0 491, Jalan Keluli, Pasir Gudang Industrial Estate,

81700 Pasir Gudang, Johor, Malaysia.

arkema.com - arkemacoatingresins.com

ARKEMA
INNOVATIVE CHEMISTRY