

CHEMPOL® 801-0066

Long Oil Alkyd

Description	Long oil soya alkyd	
Typical Properties*	Total Solids, % by weight	99
	Solvent	None
	Viscosity GH, as Supplied	Z1-Z3
	Reduced, 85% in Texanol	V-X
	Weight/Gallon (lbs)	8.5 ± 0.1
	Acid Value (max). on Solids	10
	Color, GH (max)	7

* The physical property data listed are considered to be typical properties, not specifications.

CHEMPOL® 801-0066

Long Oil Alkyd

Product Safety

Before handling the materials listed in this bulletin, read and understand the product SDS (Safety Data Sheet) for additional information on personal protective equipment and for safety, health and environmental information. For environmental, safety and toxicological information, contact our Customer Service Department at 1-866-837-5532 to find an SDS, or visit our web site: www.coatingresins-arkema.com

No chemical should be used as or in a food, drug, medical device, or cosmetic, or in a product or process in which it may contact a food, drug, medical device, or cosmetic until the user has determined the suitability and legality of the use. Since government regulations and use conditions are subject to change, it is the user's responsibility to determine that this information is appropriate and suitable under current, applicable laws and regulations.

Coating Resins – Arkema requests that the customer read, understand, and comply with the information contained in this publication and the current SDS(s). The customer should furnish the inform

Storage and Handling

CHEMPOL® 801-0066 should be stored indoors in the original unopened and undamaged container in a dry place at a temperature between 34° F and 85° F. Exposure to direct sunlight should be avoided.



Coating Resins – Arkema
410 Gregson Dr.
Cary, NC 27511

Telephone:
1.800.777.8227

Visit our website:
coatingresins-arkema.com

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; **NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.** The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

© 2021 Arkema Inc. All rights reserved. 2/21
CHEMPOL® is a registered trademark of Arkema Inc.



Responsible Care®
Good Chemistry at Work

is a registered trademark of the American Chemistry Council Inc.